



SandWise PanelPro ® (Polyurethane System)

CHEMICAL NAME	Polyurethane system
TECHNICAL REQUIREMENTS	Weight ratio of components POLY : ISO..... 100 : 159 Optimal components temperature: 18 - 22°C Ambient temperature: 18 - 35°C Temperature of the metal plate: 20 - 40°C Temperature of the press: 30 - 50 °C
GENERAL DATA	Apparent core density: $\geq 40 \text{ kg/m}^3$ PN-EN 1802:2013-07 Steel surface should be free from dust, oil and water
APPLICATION	SandWise PanelPro is design to be used in production of sandwich panels in continuous production line with mineral wool, EPS, or PU.